



**Sydney Head Office:**  
Phone: 02 9688 1999  
Fax: 02 9896 1606  
78 – 80 Mandoon Road  
Girraween, 2145, NSW  
[sales@lacnam.com.au](mailto:sales@lacnam.com.au)

TDS 210 RFU page 1 of 2

# 210 FIDAX RFU BLACK

## Description and uses

210 Fidax RFU is an alkyd based zinc phosphate anticorrosive enamel formulated for use in dip tanks for the coating of metal objects.

210 Fidax RFU Enamel has the following features:

- Fast drying and setup.
- Recoatable.
- Tough film properties.

Typical areas of application are:

- Coils, springs etc.
- Swaybars and tools.
- Scaffolding etc.

## Technical Specifications

FINISH: Matt.

THINNERS: T102 or T104 thinners (other blends of solvents for specific use should be discussed with technical department)

VOLUME SOLIDS: 35-35%

COVERAGE: Approximately 9-10 Square metres per litre (at a D.F.T. of 40 microns).

RECOMMENDED FILM THICKNESS: 25-35 microns dry.

APPLICATION: Dipping, conventional and airless spray.

DRYING AT 25°C: Touch dry 20-30 minutes  
Hard dry overnight



**Sydney Head Office:**  
Phone: 02 9688 1999  
Fax: 02 9896 1606  
78 – 80 Mandoon Road  
Girraween, 2145, NSW  
[sales@lacnam.com.au](mailto:sales@lacnam.com.au)

TDS 210 RFU page 2 of 2

APPLICATION DETAILS – PAINTING SYSTEMS			
D.F.T. um			
System 1	1 <sup>st</sup> Coat	25-35	210 Fidax RFU Black
	2 <sup>nd</sup> Coat	25-35	210 Fidax RFU Black (optional)

D.F.T. um			
System 2	1 <sup>st</sup> Coat	5-10	258 Twin Pack Etch or 260 Key-Coat (thinner T166)
	2 <sup>nd</sup> Coat	25-35	210 Fidax RFU Black

APPLICATION DETAILS – SURFACE PREPARATION		
SUBSTRATE	DETAILS	RECOMMENDED SYSTEM
Steel	Power tool clean to AS1627.2 class 2 or abrasive blast clean to AS1627.4 Class 2	1
Aluminum and non-ferrous metals	Light abrasive blast or treat with 212 metal clean.	2

**Note:** All surfaces to be painted should be clean and free from dust, dirt, oil, grease etc. All surfaces must be free of moisture and topcoat not applied when the substrate temperature is below 5°C. Care must be taken to avoid contaminants (such as cement from scaffolding) entering dip tanks.

### Application

- Dipping tanks should be agitated regularly for optimum performance and stability. Regular addition of stabilizers is recommended.
- Reduction with thinners to achieve a suitable dipping viscosity must be performed and viscosity measured with a flow cup.
- As solvent evaporation will occur, viscosity should be monitored and thinners added when required.

### Safety Instructions

**Flammability:** Highly flammable, avoid heat and sources of ignition. Container should be earthed when pouring.

**Personal Protection:** Avoid contact with skin or eyes, wear suitable clothing such as impervious overalls, PVC or neoprene gloves, and safety goggles. Wear an approved half-face respirator suitable for organic vapor, meeting AS1715/1716.

**Engineering controls:** Ensure ventilation is adequate. When spraying, ensure product is applied in a fully functional spray-booth. Keep containers closed when not in use. Do not use near ignition sources.

Although this information is presented in good faith and compiled from sources believed to be accurate, Lacnam Paints make no representations or warranty as to the completeness or accuracy thereof. As the product's performance and suitability depends on various factors, the purchasers of our products should determine for themselves whether the product is suitable for their particular use.