



**Sydney Head Office:**  
Phone: 02 9688 1999  
Fax: 02 9896 1606  
78 – 80 Mandoon Road  
Girraween, 2145, NSW  
[sales@lacnam.com.au](mailto:sales@lacnam.com.au)

TDS 310 page 1 of 2

# 310 ENAMEL

## Quick Dry Enamel

### Description and uses

310 Enamel is an economical modified alkyd spraying enamel for use in light industrial environments where top quality exterior durability is not required.

310 Enamel has the following features:

- Fast drying and setup.
- Excellent recoating properties.
- Tough film properties.

Typical areas of application are:

- Tools, machinery, pipelines etc.
- Structural steel and sheet metal.
- Drums, trailers etc.

### Technical Specifications

**FINISH:** High gloss.

**THINNERS:** T102 or T104 thinners (T124 for electrostatic applications).

**VOLUME SOLIDS:** 35-40% depending on colour.

**COVERAGE:** Approximately 9-10 Square metres per litre (at a D.F.T. of 40 microns).

**RECOMMENDED FILM THICKNESS:** 25-45 microns dry.

**APPLICATION:** Conventional or airless spray.

**DRYING AT 25°C:** Touch dry 20-30 minutes

Recoat – 2 hours

Hard dry overnight



**Sydney Head Office:**  
 Phone: 02 9688 1999  
 Fax: 02 9896 1606  
 78 – 80 Mandoon Road  
 Girraween, 2145, NSW  
[sales@lacnam.com.au](mailto:sales@lacnam.com.au)

TDS 310 page 2 of 2

APPLICATION DETAILS – PAINTING SYSTEMS			
D.F.T. um			
System 1	1 <sup>st</sup> Coat	50	210 Metalprime (thinner T102 or T104)
	2 <sup>nd</sup> Coat	40	310 Quick Dry Enamel (thinner T102 or T104)

D.F.T. um			
System 2	1 <sup>st</sup> Coat	5-10	258 Twin Pack Etch or 260 Key-Coat (thinner T166)
	2 <sup>nd</sup> Coat	40	310 Quick Dry Enamel (thinner T102 or T104)

APPLICATION DETAILS – SURFACE PREPARATION		
SUBSTRATE	DETAILS	RECOMMENDED SYSTEM
Steel	Power tool clean to AS1627.2 class 2 or abrasive blast clean to AS1627.4 Class 2	1
Aluminum and non-ferrous metals	Light abrasive blast or treat with 212 metal clean.	2

**Note:** All surfaces to be painted should be clean and free from dust, dirt, oil, grease etc. All surfaces must be free of moisture and topcoat not applied when the substrate temperature is below 5°C.

### Application

**Conventional spray:** Thin approximately 20% with T102 or T104. Apply 2 coats wet on wet using 350-400 kPa atomizing pressure.

**Airless spray:** Thinning is not normally required, however a small amount of T102 or T104 may assist atomization.

**Clean up:** T102 or Gun and Brush Wash.

### Safety Instructions

**Flammability:** Highly flammable, avoid heat and sources of ignition. Container should be earthed when pouring.

**Personal Protection:** Avoid contact with skin or eyes, wear suitable clothing such as impervious overalls, PVC or neoprene gloves, safety goggles. Wear an approved half-face respirator suitable for organic vapor, meeting AS1715/1716.

**Engineering controls:** Ensure ventilation is adequate. When spraying, ensure product is applied in a fully functional spray-booth. Keep containers closed when not in use. Do not use near ignition sources.

Although this information is presented in good faith and compiled from sources believed to be accurate, Lacnam Paints make no representations or warranty as to the completeness or accuracy thereof. As the product's performance and suitability depends on various factors, the purchasers of our products should determine for themselves whether the product is suitable for their particular use.