



**Sydney Head Office:**  
Phone: 02 9688 1999  
Fax: 02 9896 1606  
78 – 80 Mandoon Road  
Girraween, 2145, NSW  
[sales@lacnam.com.au](mailto:sales@lacnam.com.au)

TDS 390 page 1 of 3

# 390 ENAMEL

## Air Drying Enamel

### Description and uses

390 Air Drying Enamel is a high gloss spraying enamel based on a blend of quality alkyd resins to provide a superior finish for earthmoving and agricultural equipment, and protection for metals in light industrial environments.

390 Air Drying Enamel has the following features:

- High gloss and excellent exterior durability and weathering.
- Compatible with all Lacnam Primers.
- Recoatable.
- Enhanced drying, gloss, durability and masking properties with addition of 298 Enamel Additive.

Typical areas of application are:

- Machinery, cranes, implements and forklifts.
- Structural steel etc.
- Trucks, tractors and trailers.

### Technical Specifications

FINISH: High gloss.

THINNERS: T102 or T104 (or T124 for electrostatic application).

VOLUME SOLIDS: 35-40% depending on colour.

COVERAGE: Approximately 9-10 Square metres per litre (at a D.F.T. of 40 microns).

RECOMMENDED FILM THICKNESS: 25-40 microns dry.

APPLICATION: Conventional or airless spray.

DRYING AT 25°C: Tack free 2-4 hours

Recoat– after overnight drying

Hard dry- overnight

**Note:** If this product is to be used where masking up and repainting, or where quicker drying is required, the use of 298 Enamel Additive is recommended. Refer to technical data sheet for 298 Enamel Additive before use.



**Sydney Head Office:**  
 Phone: 02 9688 1999  
 Fax: 02 9896 1606  
 78 – 80 Mandoon Road  
 Girraween, 2145, NSW  
[sales@lacnam.com.au](mailto:sales@lacnam.com.au)

TDS 390 page 2 of 3

APPLICATION DETAILS – PAINTING SYSTEMS			
D.F.T. um			
System 1	1 <sup>st</sup> Coat	50	210 Metalprime (thinner T102 or T104)
	2 <sup>nd</sup> Coat	25-40	390 Air Dry Enamel (thinner T104 or T104)
	3 <sup>rd</sup> Coat	25-40	Optional

D.F.T. um			
System 2	1 <sup>st</sup> Coat	5-10	258 Twin Pack Etch or 260 Key-Coat (thinner T166)
	2 <sup>nd</sup> Coat	25-40	390 Air Dry Enamel (thinner T104 or T104)
	3 <sup>rd</sup> Coat	25-40	Optional

D.F.T. um			
System 3	1 <sup>st</sup> Coat	5-10	722 Iso-Free Primer (thinner T154 or slow T156 or T159)
	2 <sup>nd</sup> Coat	25-40	390 Air Dry Enamel (thinner T104 or T104)
	3 <sup>rd</sup> Coat	25-40	Optional

APPLICATION DETAILS – SURFACE PREPARATION		
SUBSTRATE	DETAILS	RECOMMENDED SYSTEM
Steel	Power tool clean to AS1627.2 class 2 or abrasive blast clean to AS1627.4 Class 2	1 or 3
Aluminum and non-ferrous metals	Light abrasive blast or treat with 212 metal clean.	2 or 3
Previously painted surfaces	Lightly sand glossy areas, wash down with cleaning solvent.	2

**Note:** All surfaces to be painted should be clean and free from dust, dirt, oil, grease etc. All surfaces must be free of moisture and topcoat not applied when the substrate temperature is below 5°C.

### Application

**Conventional spray:** Thin approximately 20-25% with T102 or T104. Apply 2 coats wet on wet, allowing 15 minutes between coats using 350-400 kPa atomizing pressure.

**Airless spray:** Thin approximately 50-10% with T102, apply at approximately 15 mPa atomizing pressure.

**Clean up:** T102, T104 or Gun and Brush Wash.



**Sydney Head Office:**  
Phone: 02 9688 1999  
Fax: 02 9896 1606  
78 – 80 Mandoon Road  
Girraween, 2145, NSW  
[sales@lacnam.com.au](mailto:sales@lacnam.com.au)

TDS 390 page 3 of 3

### **Safety Instructions**

Flammability: Highly flammable, avoid heat and sources of ignition. Container should be earthed when pouring.

Personal Protection: Avoid contact with skin or eyes, wear suitable clothing such as impervious overalls, PVC or neoprene gloves, and safety goggles. Wear an approved half-face respirator suitable for organic vapor, meeting AS1715/1716.

Engineering controls: Ensure ventilation is adequate. When spraying, ensure product is applied in a fully functional spray-booth. Keep containers closed when not in use. Do not use near ignition sources.

Although this information is presented in good faith and compiled from sources believed to be accurate, Lacnam Paints make no representations or warranty as to the completeness or accuracy thereof. As the product's performance and suitability depends on various factors, the purchasers of our products should determine for themselves whether the product is suitable for their particular use.